


Viledon® NEXX, NEXX as

Made with Evolon®



Technical data			
Filter media	NEXX	NEXX as	Test specification
Weight [g/m ²]	240	240	DIN EN 29073 - 01
Thickness [mm]	1.0	1.0	DIN EN ISO 9073 - 2
Air permeability [l/dm ² min at 2 mbar]	100	80	DIN EN ISO 9237
Fibres	PES/PA Hydroentangled microfilaments	PES/PA Hydroentangled microfilaments	-
Temperature resistance [°C]	150	150	-
Tensile strength [N/5 cm]			
Longitudinal	> 700	> 700	DIN EN 29073/3
Transversal	> 800	> 800	
Elongation [%]			
Longitudinal	ca. 35	ca. 35	DIN EN 29073/3
Transversal	ca. 35	ca. 35	
Mullen burst [MPa]	> 15	> 15	ASTM D 3786 - 2001
Additional features	-	Antistatic print	-

The figures given are mean values subject to tolerances due to the normal production variations.
The accuracy of the data given when applied to individual cases requires our express written confirmation.
Subject to technical changes.

viledon®
NEXX
Made with Evolon®